

# **Installation Instructions for Polyaspartics**

## **(TKO5000)**

### **Tools/Equipment Needed**

- Brushes for cutting in edges
- 5 mil or 10 mil 18" roller sleeves plus cage with pole attachment
- Drill with mixing paddle
- Mixing pails
- Small pail for use with brush to do edges
- Shop vac
- Broom
- Gloves for mixing and coating
- Spiked shoes
- Garbage bags
- Small tarp for mixing station
- Paint sticks

### **Installation Steps**

1. Prepare surface for proper bonding by diamond grinding, shot blasting or acid etching
2. Vacuum floor to ensure all dust is removed (this is critical for adhesion of the coating to the concrete)
3. Prepare all tools necessary for coating (drill, pails, brush, rollers, tray, gloves, etc)
4. Mix desired amounts of parts A and B in a clean mixing pail. Immediately begin brushing edges and squeegee out material to evenly coat floor. Avoid any puddles. Allow to dry.
5. Pour all mixed product on the floor in ribbons saving some for cutting in and use squeegee to spread the product leaving only enough to cover the floor. For the first coat, push the flat squeegee at an even speed with a downward pressure. The first coat should be approximately 10-12 mils (133-160 square feet per gallon). Back rolling is not necessary if coat is applied thin and even, not leaving puddles or high spots. Never mix more product than you can apply in a 15-20 minute period. Have someone else cut in around the perimeter and around poles or equipment with a brush
6. Once the coating is spread out, back roll the product using the 18" roller to a smooth and uniform appearance. Avoid leaving any puddles.
7. Remember you must maintain a wet edge at all times - do not let an area start to dry otherwise you will end up with lines where the wet and the dry product meets.
8. For the build coat, use the same steps as in the first coat, and apply at a rate of 10-15 mils (160-107 square feet per gallon)

**\*\*\*Remember to always check to see what the mix ratio is before mixing.**